

**TEST REPORT**

**Client:** Supacolor USA  
16918 Gramercy Pl  
Gardena, CA 90247  
**Attention:** Rum Walia  
**E-Mail:** rum@supacolor.com

**Sample Description as Declared :**

Sample Description : Wearable Transfer On 100% Cotton Shirt  
Color : Black  
Style # : 5026  
Fabric/Garment Weight : 6.5 oz  
Fiber Content : 100% Cotton  
No. of Samples: 3  
End Use : Not Provided  
Care Instructions : Machine Wash Cold With Like Colours, Do Not Bleach, Line Dry In Shade, Do Not Tumble Dry, Do Not Iron If Printed, Do Not Dryclean.  
Sample Received Date : February 15, 2021  
Final Confirmation Received Date: February 17, 2021  
Report Completion Date : April 8, 2021



**For and on behalf of  
Intertek Products Group North America:**

**Intertek North America**  
545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

**Test Performed As Requested by Client:**

**^ AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

Sample Description: Wearable Transfer on 100% Cotton Shirt

**After 10 Cycles**

Machine washed via procedure in AATCC TM150-2018t

Washing Conditions: Machine Wash Cold 80°F, Normal Cycle, Line Dry, AATCC W/Brightener, 4.0 Lbs Load, AATCC Type 3 Ballast(50% Cotton/ 50% Polyester)

**Appearance Change Results:**

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Other Visual Evaluation:</b>	
Delamination/Peeling (Requirement: No Delamination/Peeling)	Satisfactory
Embellishment Cracking (Requirement: No Requirement)	Satisfactory
Embellishment Puckering (Requirement: No Requirement)	Satisfactory

**After 10 Cycles**



**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

**^ AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

Sample Description: Wearable Transfer on 100% Cotton Shirt

**After 20 Cycles**

Machine washed via procedure in AATCC TM150-2018t

Washing Conditions: Machine Wash Cold 80°F, Normal Cycle, Line Dry, AATCC W/Brightener, 4.0 Lbs Load, AATCC Type 3 Ballast(50% Cotton/ 50% Polyester)

Appearance Change Results:

Color Change:	Grade:
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

Other Visual Evaluation:	
Delamination/Peeling (Requirement: No Delamination/Peeling)	Satisfactory
Embellishment Cracking (Requirement: No Requirement)	Satisfactory
Embellishment Puckering (Requirement: No Requirement)	Satisfactory

After 20 Cycles



**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

**^ AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

Sample Description: Wearable Transfer on 100% Cotton Shirt

**After 30 Cycles**

Machine washed via procedure in AATCC TM150-2018t

Washing Conditions: Machine Wash Cold 80°F, Normal Cycle, Line Dry, AATCC W/Brightener, 4.0 Lbs Load, AATCC Type 3 Ballast(50% Cotton/ 50% Polyester)

Appearance Change Results:

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Other Visual Evaluation:</b>	
Delamination/Peeling (Requirement: No Delamination/Peeling)	Satisfactory
Embellishment Cracking (Requirement: No Requirement)	Satisfactory
Embellishment Puckering (Requirement: No Requirement)	Satisfactory

After 30 Cycles



**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



TESTING LABORATORY  
AT-1348

**^ AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

Sample Description: Wearable Transfer on 100% Cotton Shirt

**After 40 Cycles**

Machine washed via procedure in AATCC TM150-2018t

Washing Conditions: Machine Wash Cold 80°F, Normal Cycle, Line Dry, AATCC W/Brightener, 4.0 Lbs Load, AATCC Type 3 Ballast(50% Cotton/ 50% Polyester)

Appearance Change Results:

Color Change:	Grade:
Color Change – Print (if applicable) (Requirement: 3.5)	4.5
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

Other Visual Evaluation:	
Delamination/Peeling (Requirement: No Delamination/Peeling)	Satisfactory
Embellishment Cracking (Requirement: No Requirement)	Satisfactory
Embellishment Puckering (Requirement: No Requirement)	Satisfactory

After 40 Cycles



**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

**^ AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

Sample Description: Wearable Transfer on 100% Cotton Shirt

**After 50 Cycles**

Machine washed via procedure in AATCC TM150-2018t

Washing Conditions: Machine Wash Cold 80°F, Normal Cycle, Line Dry, AATCC W/Brightener, 4.0 Lbs Load, AATCC Type 3 Ballast(50% Cotton/ 50% Polyester)

Appearance Change Results:

Color Change:	Grade:
Color Change – Print (if applicable) (Requirement: 3.5)	Grey 4.0, Other 4.5
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

Other Visual Evaluation:	
Delamination/Peeling (Requirement: No Delamination/Peeling)	Satisfactory
Embellishment Cracking (Requirement: No Requirement)	Satisfactory
Embellishment Puckering (Requirement: No Requirement)	Satisfactory

After 50 Cycles



**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

**^ AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

Sample Description: Wearable Transfer on 100% Cotton Shirt

**After 60 Cycles**

Machine washed via procedure in AATCC TM150-2018t

Washing Conditions: Machine Wash Cold 80°F, Normal Cycle, Line Dry, AATCC W/Brightener, 4.0 Lbs Load, AATCC Type 3 Ballast(50% Cotton/ 50% Polyester)

Appearance Change Results:

Color Change:	Grade:
Color Change – Print (if applicable) (Requirement: 3.5)	Grey 4.0, Other 4.5
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

Other Visual Evaluation:	
Delamination/Peeling (Requirement: No Delamination/Peeling)	Satisfactory
Embellishment Cracking (Requirement: No Requirement)	Satisfactory
Embellishment Puckering (Requirement: No Requirement)	Satisfactory

\*Additional Comment: Slight wash off of grey print coating observed.

After 60 Cycles



**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

**^ AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

Sample Description: Wearable Transfer on 100% Cotton Shirt

**After 70 Cycles**

Machine washed via procedure in AATCC TM150-2018t

Washing Conditions: Machine Wash Cold 80°F, Normal Cycle, Line Dry, AATCC W/Brightener, 4.0 Lbs Load, AATCC Type 3 Ballast(50% Cotton/ 50% Polyester)

Appearance Change Results:

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Print (if applicable) (Requirement: 3.5)	Grey 4.0, Other 4.5
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Other Visual Evaluation:</b>	
Delamination/Peeling (Requirement: No Delamination/Peeling)	Satisfactory
Embellishment Cracking (Requirement: No Requirement)	<b>Unsatisfactory</b>
Embellishment Puckering (Requirement: No Requirement)	Satisfactory

\*Additional Comment: Moderate wash off of grey coating print observed.

**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



TESTING LABORATORY  
AT-1348



After 70 Cycles



**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

**^ AATCC TS-008 – Appearance of Apparel and Other Textile Products After Laundering**

Sample Description: Wearable Transfer on 100% Cotton Shirt

**After 80 Cycles**

Machine washed via procedure in AATCC TM150-2018t

Washing Conditions: Machine Wash Cold 80°F, Normal Cycle, Line Dry, AATCC W/Brightener, 4.0 Lbs Load, AATCC Type 3 Ballast(50% Cotton/ 50% Polyester)

Appearance Change Results:

<b>Color Change:</b>	<b>Grade:</b>
Color Change – Print (if applicable) (Requirement: 3.5)	Grey 4.0, Other 4.5
Self/Cross Staining (if applicable) (Requirement: 4.5)	4.5

<b>Other Visual Evaluation:</b>	
Delamination/Peeling (Requirement: No Delamination/Peeling)	Satisfactory
Embellishment Cracking (Requirement: No Requirement)	<b>Unsatisfactory</b>
Embellishment Puckering (Requirement: No Requirement)	Satisfactory

**\*Additional Comment: Noticeable wash off of grey coating print observed.**

**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348

After 80 Cycles



**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



TESTING LABORATORY  
AT-1348

***“Report includes non-accredited test results. The test(s) marked with a carat (^) are not covered by our current ISO/IEC 17025:2017 scope of accreditation.”***

*The test results stated in this report relate only to the item(s) tested. This test report may not be reproduced except in full, without written approval of Intertek.*

.....

*If you need assistance in interpreting these results or if you have any questions,  
please feel free to call Customer Service Department*

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.*

**Intertek North America**

545 E Algonquin Road, Suite F  
Arlington Heights, Illinois 60005  
Telephone: 847-871-1020 Fax: 847-439-6156



AT-1348